


WATER VAPOR TRANSMISSION BY ASTM E 96

SAMPLE THICKNESS (in)	(g/hr)	WVTR (g/hr m ²)	PERMEANCE	
			(g/PA•s•m ²)	PERMS
0.02463	- 0.0057			
0.01861	- 0.0070			
0.01971	- 0.0070			
AV = 0.0209	- 0.0067	1.4776	2.59 x 10 ⁻⁷	4.53
± 0.0032	± 0.0007	± 0.154	± 0.27 x 10 ⁻⁷	± 0.57

DISH #3 HT100F POLYUREA PRODUCT

DISH #2 HT100F POLYUREA PRODUCT
